



RSL - RESTRICTED SUBSTANCE LIST

2026 Version 2 - Issued June 2026

Test No.	Substance	CAS No.	Superdry RSL Limits Component Materials in Finished Product	Test method
1	Acetophenone and 2-Phenyl-2-Propanol			
	Acetophenone	98-86-2	50 ppm each	Extraction in acetone or methanol GC/MS, sonication for 30 minutes at 60° C Extraction in acetone or methanol GC/MS or LC/MS, sonication for 30 minutes at room temperature
	2-Phenyl-2-Propanol	617-94-7	50 ppm each	
	Acetophenone Azine	729-43-1	50 ppm each	
2	Acidic and Alkaline Substances			
	pH value in Textiles	N/A	4.0 - 7.5	Textiles and synthetic coated fabrics: EN ISO 3071:2020 Leather: EN ISO 4045:2018
	pH value in Leather (Chrome Tanned)	N/A	3.5 - 5.5 Important: Egypt, Morocco, and the Gulf Cooperation Council (GCC) require pH for leather not lower than 3.5 - which must be followed for relevant orders	
	pH Other	N/A	3.5 -7.5	
3	Alkylphenols (APs) & Alkylphenol Ethoxylates (APEOs) including all isomers.			
	Nonylphenol (NP), mixed isomers	Various	Total APs: 10 ppm	Textiles and Leather: EN ISO 21084:2019 Polymers and all other materials: 1 g sample/20 mL THF, sonication for 60 minutes at 70° C, analysis according to EN ISO 21084:2019 Down (China market only): GB/T 23322-2018 for compliance with GB/T 14272-2021 Leather: Sample prep and analysis using EN ISO 18218-1:2023 with quantification according to EN ISO 18254-1:2016 Down (China market only): GB/T 23322-2018 for compliance with GB/T 14272-2021
	Octylphenol (OP), mixed isomers	Various		
	Nonylphenol ethoxylates (NPEOs)	Various	Total APEOs: 100 ppm	
	Octylphenol ethoxylates (OPEOs)	Various		
			Total APs + APEOs: 100 ppm	
4	Azo-amines and Arylamine Salts			
	4-Aminobiphenyl	92-67-1	20 ppm each	All materials except leather: EN ISO 14362-1:2017 Leather: EN ISO 17234-1:2024 p-Aminoazobenzene: All materials except leather: EN ISO 14362-3:2017 Leather: EN ISO 17234-2:2011
	Benzidine	92-87-5	20 ppm each	
	4-Chloro-o-toluidine	95-69-2	20 ppm each	
	2-Naphthylamine	91-59-8	20 ppm each	
	o-Aminoazotoluene	97-56-3	20 ppm each	
	2-Amino-4-nitrotoluene	99-55-8	20 ppm each	
	p-Chloraniline	106-47-8	20 ppm each	
	2,4-Diaminoanisole	615-05-4	20 ppm each	
	4,4'-Diaminodiphenylmethane	101-77-9	20 ppm each	
	3,3'-Dichlorobenzidine	91-94-1	20 ppm each	
	3,3'-Dimethoxybenzidine	119-90-4	20 ppm each	
	3,3'-Dimethylbenzidine	119-93-7	20 ppm each	
	3,3'-dimethyl-4,4'-diaminodiphenylmethane	838-88-0	20 ppm each	
	p-Cresidine	120-71-8	20 ppm each	
	4,4'-Methylen-bis(2-chloraniline)	101-14-4	20 ppm each	
	4,4'-Oxydianiline	101-80-4	20 ppm each	
	4,4'-Thiodianiline	139-65-1	20 ppm each	
	o-Toluidine	95-53-4	20 ppm each	
	2,4-Toluenediamine	95-80-7	20 ppm each	
	2,4,5-Trimethylaniline	137-17-7	20 ppm each	
	2,4 Xyldine	95-68-1	20 ppm each	

	2,6 Xylidine	87-62-7	20 ppm each	
	2-Methoxyaniline (= o-Anisidine)	90-04-0	20 ppm each	
	p-Aminoazobenzene	60-09-3	20 ppm each	
	4-Chloro-o-toluidinium chloride	3165-93-3	20 ppm each	
	2-Naphthylammoniumacetate	553-00-4	20 ppm each	
	4-Methoxy-m-phenylene diammonium sulphate	39156-41-7	20 ppm each	
	2,4,5-Trimethylaniline hydrochloride	21436-97-5	20 ppm each	
5	Bisphenols			
	Bisphenol-A (BPA)	80-05-7	Drinking cups: 0.05 ppm 	

	p-Chlorobenzotrichloride	5216-25-1		10 ppm Important: The Gulf Cooperation Council (GCC) maintains a limit of 1 ppm for 1,2-Dichlorobenzene intextiles - which must be followed for relevant orders.
	Benzotrichloride	98-07-7		
	Benzyl Chloride	100-44-7		
	1,2-Dichlorobenzene	95-50-1		
9	Dimethylfumarate			
	Dimethylfumarate (DMFu)	624-49-7	0.1 ppm	All materials: ISO 16186:2021
10	Dyes (Forbidden and Disperse)			
	C.I. Disperse Blue 1	2475-45-8	30 ppm each	All materials: DIN 54231:2022
	C.I. Disperse Blue 3	2475-46-9	30 ppm each	
	C.I. Disperse Blue 7	3179-90-6	30 ppm each	
	C.I. Disperse Blue 26	3860-63-7	30 ppm each	
	C.I. Disperse Blue 35A	56524-77-7	30 ppm each	
	C.I. Disperse Blue 35B	56524-76-6	30 ppm each	
	C.I. Disperse Blue 102	12222-97-8	30 ppm each	
	C.I. Disperse Blue 106	12223-01-7	30 ppm each	
	C.I. Disperse Blue 124	61951-51-7	30 ppm each	
	C.I. Disperse Brown 1	23355-64-8	30 ppm each	
	C.I. Disperse Orange 1	2581-69-3	30 ppm each	
	C.I. Disperse Orange 3	730-40-5	30 ppm each	
	C.I. Disperse Orange 11	82-28-0	30 ppm each	
	C.I. Disperse Orange 37/76/59	12223-33-5	30 ppm each	
		13301-61-6		
		51811-42-8		
	C.I. Disperse Orange 149	85136-74-9	30 ppm each	
	C.I. Disperse Red 1	2872-52-8	30 ppm each	
	C.I. Disperse Red 11	2872-48-2	30 ppm each	
	C.I. Disperse Red 17	3179-89-3	30 ppm each	
	C.I. Disperse Red 151	61968-47-6	30 ppm each	
	C.I. Disperse Yellow 1	119-15-3	30 ppm each	
	C.I. Disperse Yellow 3	2832-40-8	30 ppm each	
	C.I. Disperse Yellow 7	6300-37-4	30 ppm each	
	C.I. Disperse Yellow 9	6373-73-5	30 ppm each	
	C.I. Disperse Yellow 23	6250-23-3	30 ppm each	
	C.I. Disperse Yellow 39	12236-29-2	30 ppm each	
	C.I. Disperse Yellow 49	54824-37-2	30 ppm each	
	C.I. Disperse Yellow 49	6858-49-7	30 ppm each	
	C.I. Disperse Yellow 56	54077-16-6	30 ppm each	
	C.I. Acid Red 26	3761-53-3	30 ppm each	
	C.I. Basic Red 9	569-61-9	30 ppm each	
	C.I. Basic Green 4	569-64-2	30 ppm each	
	C.I. Basic Green 4	2437-29-8	30 ppm each	
	C.I. Basic Green 4	10309-95-2	30 ppm each	
	C.I. Basic Violet 3	548-62-9	30 ppm each	
	C.I. Basic Violet 14	632-99-5	30 ppm each	
	C.I. Basic Blue 26	2580-56-5	30 ppm each	
	C.I. Direct Black 38	1937-37-7	30 ppm each	
	C.I. Direct Blue 6	2602-46-2	30 ppm each	
	C.I. Direct Red 28	573-58-0	30 ppm each	
	C.I. Direct Brown 95	16071-86-6	30 ppm each	
	4-Dimethylaminoazobenzene (Solvent Yellow 2)	60-11-7	30 ppm each	
	C.I. Solvent Blue 4	6786-83-0	30 ppm each	
	4,4'-bis(dimethylamino)-4''-(methylamino)trityl alcohol	561-41-1	30 ppm each	
11	Dyes, Navy Blue			
	Component 1: C39H23ClCrN7O12S.2Na	118685-33-9	30 ppm each	All materials: DIN 54231:2022
	Component 2: C46H30CrN10O20S2.3Na	Not allocated	30 ppm each	
12	Brominated and Organophosphorus substances			
	Decabromodiphenyl ethane (DBDPE)	84852-53-9	10 ppm each	All materials: EN ISO 17881-1:2016
	Pentabromodiphenyl ether (PentaBDE)	32534-81-9	10 ppm each	
	Octabromodiphenyl ether (OctaBDE)	32536-52-0	10 ppm each	
	Decabromodiphenyl ether (DecaBDE)	1163-19-5	10 ppm each	
	All other Polybrominated diphenyl ethers (PBDEs)	Various	10 ppm each	
	Tetrabromobisphenol A (TBBP A)	79-94-7	10 ppm each	
	Polybromobiphenyls (PBB)	59536-65-1	10 ppm each	
	Hexabromocyclododecane (HBCDD)	3194-55-6	10 ppm each	
	2,2-bis(bromomethyl)-1,3-propanediol (BBMP)	3296-90-0	10 ppm each	
	Tris(1,3-dichloro-isopropyl) phosphate (TDCPP)	13674-87-8	10 ppm each	
	Trixylyl phosphate (TXP)	25155-23-1	10 ppm each	All materials: EN ISO 17881-2:2016
	Tris(2,3,-dibromopropyl) phosphate (TRIS)	126-72-7	10 ppm each	
	Tris(1-aziridinyl)phosphine oxide) (TEPA)	545-55-1	10 ppm each	
	Tris(2-chloroethyl)phosphate (TCEP)	115-96-8	10 ppm each	
	Bis(2,3-dibromopropyl) phosphate (BDBPP)	5412-25-9	10 ppm each	
	Triphenyl phosphate (TPP)	115-86-6	500 ppm	
13	Fluorinated Greenhouse Gases			
	See Regulation (EU) 2024/573 for a complete list.	Various	0.1 ppm each (prohibited from use)	Sample preparation: Purge and trap — thermal desorption or SPME Measurement: GC/MS

14	Formaldehyde			
	Formaldehyde	50-00-0	Adults and Children: 75 ppm Children's Leather: 50ppm	All materials except leather: JIS L 1041-2011 A (Japan Law 112) or EN ISO 14184-1:2011 Leather: EN ISO 17226-1:2021 or EN ISO 17226-2:2019. In case of interferences/doubts, proceed with EN ISO 17226-1:2021. EN ISO 17226-1:2021 can be used on its own.
15	Chromium VI in Leather			
	Chromium VI	18540-29-9	Extractable Leather: 3 ppm	Textiles: EN 16711-2:2015 with EN ISO 17075-1:2017 if Cr is detected Leather: EN ISO 17075-1:2017 and EN ISO 17075-2:2017 for confirmation in case the extract causes interference. Alternatively, EN ISO 17075-2:2017 may be used on its own. Aging test: ISO 10195:2018
16a	Heavy Metals (Non-Jewellery) Extractable			
	Antimony (Sb)	7440-36-0	30 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Arsenic (As)	7440-38-2	0.2 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Barium (Ba)	7440-39-3	1000 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Cadmium (Cd)	7440-43-9	0.1 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Chromium (Cr)	7440-47-3	2 ppm Textiles	Textiles: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Chromium VI	18540-29-9	1 ppm Textiles	Textiles: EN 16711-2:2015 with EN ISO 17075-1:2017 if Cr is detected Leather: EN ISO 17075-1:2017 and EN ISO 17075-2:2017 for confirmation in case the extract causes interference. Alternatively, EN ISO 17075-2:2017 may be used on its own. Aging test: ISO 10195:2018
	Cobalt (Co)	7440-48-4	Adults: 4 ppm, Children and Babies: 1ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Copper (Cu)	7440-50-8	Adults: 50 ppm (Copper is exempt from restriction limits in metal parts). Children and Babies: 25 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Lead (Pb)	7439-92-1	Adults: 4 ppm, Children and Babies: 0.2 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Mercury (Hg)	7439-97-6	0.02 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Nickel (Ni)	7440-02-0	1 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
	Selenium (Se)	7782-49-2	500 ppm	All materials except leather: EN 16711-2:2015 Leather: EN ISO 17072-1:2019
16b	Heavy Metals (Non-Jewellery) Total Content			
	Arsenic (As)	7440-38-2	100 ppm	All materials except leather: EN 16711-1:2015 Leather: EN ISO 17072-2:2022
	Cadmium (Cd)	7440-43-9	40 ppm	All materials except leather: EN 16711-1:2015 Leather: EN ISO 17072-2:2022
	Lead (Pb)	7439-92-1	90 ppm	Non-metal: CPSC-CH-E1002-08.3 Metal: CPSC-CH-E1001-08.3 Lead in paint and surface coatings: CPSC-CH-E1003-09.1
	Mercury (Hg)	7439-97-6	0.5 ppm	All materials except leather: EN 16711-1:2015 Leather: EN ISO 17072-2:2022
17	Nickel Release			
	Nickel (Ni)	7440-02-0	0.5 µg/cm²/week	Release: EN 12472:2020 and EN 1811:2023 Release (eyewear frames): EN 16128:2025
18	Monomers			
	Styrene, Free	100-42-5	500 ppm	Extraction in Methanol GC/MS, sonication at 60° C for 60 minutes
	Vinyl Chloride	75-01-4	1 ppm	
19	N-Nitrosamines			

	N-nitrosodimethylamine (NDMA)	62-75-9	0.5 ppm each	EN ISO 19577:2019 with LC/MS/MS verification if positive
	N-nitrosodiethylamine (NDEA)	55-18-5	0.5 ppm each	
	N-nitrosodipropylamine (NDPA)	621-64-7	0.5 ppm each	
	N-nitrosodibutylamine (NDBA)	924-16-3	0.5 ppm each	
	N-nitrosopiperidine (NPIP)	100-75-4	0.5 ppm each	
	N-nitrosopyrrolidine (NPYR)	930-55-2	0.5 ppm each	
	N-nitrosomorpholine (NMOR)	59-89-2	0.5 ppm each	
	N-nitroso N-methyl N-phenylamine (NMPHa)	614-00-6	0.5 ppm each	
	N-nitroso N-ethyl N-phenylamine (NEPhA)	612-64-6	0.5 ppm each	
20	Organotin Compounds			
	Tributyltin (TBT)	Various	0.5 ppm each	All materials: ISO 16179:2025 or EN ISO 22744-1:2020
	Triphenyltin (TPhT)	Various	0.5 ppm each	
	Dibutyltin (DBT)	Various	1 ppm each	
	Diocetyltn (DOT)	Various	1 ppm each	
	Monobutyltin (MBT)	Various	1 ppm each	
	Tricyclohexyltin (TCyHT)	Various	1 ppm each	
	Trimethyltin (TMT)	Various	1 ppm each	
	Triocetyltn (TOT)	Various	1 ppm each	
	Tripropyltin (TPT)	Various	1 ppm each	
	Dimethyltin (DMT)	Various	Other Organotins: 1 ppm each	
	Diphenyltin (DPhT)	Various	Other Organotins: 1 ppm each	
	Dipropyltin (DPT)	Various	Other Organotins: 1 ppm each	
	Monomethyltin (MMT)	Various	Other Organotins: 1 ppm each	
	Monophenyltin (MPHT)	Various	Other Organotins: 1 ppm each	
	Tetrabutyltin (TeBT)	1461-25-2	Other Organotins: 1 ppm each	
	Tetraethyltin (TeET)	597-64-8	Other Organotins: 1 ppm each	
	Tetraocetyltn (TeOT)	3590-84-9	Other Organotins: 1 ppm each	
21	Ortho-phenylphenol			
	Ortho-phenylphenol (OPP)	90-43-7	1000 ppm, 25ppm for Children	All materials: EN 17134-2:2023
22	Ozone-depleting Substances			
	See Regulation (EU) 2024/590 for a complete list.	Various	5 ppm (prohibited from use)	All materials: GC/MS headspace 120° C for 45 minutes
23	Per- and Polyfluoroalkyl Substances (PFAS)			
	All PFAS as measured by total organic fluorine	Various	50 ppm	EN 14582:2016 or ASTM D7359:2023 or EN 17813:2023
	Perfluorooctane Sulfonate (PFOS) and its salts	Various as below:	25 ppb total	
	Didecyltrimethyl ammonium perfluorooctane sulfonate (PFOS-N(C ₁₀ H ₂₁) ₂ (CH ₃) ₂)	251099-16-8	PFOS and Its Salts Total: 25 ppb (prohibited from use)	
	Perfluorooctanesulfonic acid (PFOS)	1763-23-1		
	Perfluorooctanesulfonic acid, potassium salt (PFOS-K)	2795-39-3		
	Perfluorooctanesulfonic acid, lithium salt (PFOS-Li)	29457-72-5		
	Perfluorooctanesulfonic acid, ammonium salt (PFOS-NH ₄)	29081-56-9		
	Perfluorooctane sulfonate diethanolamine salt (PFOS-NH(OH) ₂)	70225-14-8		
	Perfluorooctanesulfonic acid, tetraethylammonium salt (PFOS-N(C ₂ H ₅) ₄)	56773-42-3		
	PFOS-related substances	Various as below:	1000 ppb total	
	N-Ethylperfluoro-1-octanesulfonamide (N-Et-FOSA)	4151-50-2	PFOs-related Substances Total: 1000ppb total	
	N-Methylperfluoro-1-octanesulfonamide (N-Me-FOSA)	31506-32-8		
	2-(N-Ethylperfluoro-1-octanesulfonamido)-ethanol (N-Et-FOSE)	1691-99-2		
	2-(N-Methylperfluoro-1-octanesulfonamido)-ethanol (N-Me-FOSE)	24448-09-7		
	Perfluoro-1-octanesulfonyl fluoride (POSF)	307-35-7		
	Perfluorooctane sulfonamide (PFOSA)	754-91-6		
	Perfluorooctanoic Acid (PFOA) and Its Salts	Various as below:	25 ppb total	
	Perfluorooctanoic acid (PFOA)	335-67-1	PFOA and Its Salts Total: 25 ppb (prohibited from use)	
	Sodium perfluorooctanoate (PFOA-Na)	335-95-5		
	Potassium perfluorooctanoate (PFOA-K)	2395-00-8		
	Silver perfluorooctanoate (PFOA-Ag)	335-93-3		
	Perfluorooctanoyl fluoride (PFOA-F)	335-66-0		
	Ammonium pentadecafluorooctanoate (APFO)	3825-26-1		
	PFOA-related Substances	Various as below:	1000 ppb total	
	1H,1H,2H,2H-Perfluorodecanesulfonic acid (8:2 FTS)	39108-34-4	PFOA-related Substances Total: 1000ppb total	
	Methyl perfluorooctanoate (Me-PFOA)	376-27-2		
	Ethyl perfluorooctanoate (Et-PFOA)	3108-24-5		
	2-Perfluorooctylethanol (8:2 FTOH)	678-39-7		
	1H,1H,2H,2H-Perfluorodecyl acrylate (8:2 FTA)	27905-45-9		
	1H,1H,2H,2H-Perfluorodecyl methacrylate (8:2 FTMA)	1996-88-9		
	2H,2H-Perfluorodecanoic acid (H2PFDA)	27854-31-5		
	Perfluorohexane-1-sulphonic acid (PFHxS) and Its Salts	Various as below:	25 ppb total	Textiles, synthetic coated fabrics, excluding leathers and polymers: EN 17681-1:2025 alkaline hydrolysis Leather: EN ISO 23702-1:2023 Polymers: EN ISO 23702-1:2023 using THF extraction followed by methanol precipitation (1:1).
	Perfluorohexane Sulfonic acid (PFHxS)	355-46-4	PFHxS and Its Salts Total: 25 ppb (prohibited from use)	
	Perfluorohexane Sulfonic acid, potassium salt (PFHxS-K)	3871-99-6		
	Perfluorohexane Sulfonic acid, lithium salt (PFHxS-Li)	55120-77-9		
	Perfluorohexane Sulfonic acid, ammonium salt (PFHxS-NH4)	68259-08-5		
	Perfluorohexane Sulfonic acid, sodium salt (PFHxS-Na)	82382-12-5		
	PFHxS-related Substances	Various as below:	1000 ppb total	
	N-Methylperfluoro-1-hexanesulfonamide (N-Me-FHxSA)	68259-15-4	PFHxS-related Substances Total: 1 ppm (prohibited from use)	
	Perfluorohexane sulfonamide (PFHxSA)	41997-13-1		
	C9-C14 Perfluorocarboxylic acids (PFCAs) and Their Salts	Various as below:	25 ppb total	

Perfluorononanoic Acid (PFNA, C9-PFCA)	375-95-1	C9-C14 PFCA and Their Salts Total: 25 ppb (prohibited from use)
Perfluorodecanoic Acid (PFDA, C10-PFCA)	335-76-2	
Perfluoroundecanoic Acid (PFUnA, C11-PFCA)	2058-94-8	
Perfluorododecanoic Acid (PFDoA, C12-PFCA)	307-55-1	
Perfluorotridecanoic Acid (PFTrDA, C13-PFCA)	72629-94-8	
Perfluorotetradecanoic Acid (PFTeDA, C14-PFCA)	376-06-7	
Perfluoro-3-7-dimethyloctanecarboxylate (PF-3,7-DMOA)	172155-07-6	
C9-C14 PFCA-related substances	Various as below:	260 ppb total
1H,1H,2H,2H-Perfluorododecyl acrylate (10:2 FTA)	17741-60-5	C9-C14 PFCA-related Substances Total: 260 ppb (prohibited from use)
1H,1H,2H,2H-Perfluorododecyl methacrylate (10:2 FTMA)	2144-54-9	
1H,1H,2H,2H-Perfluorododecanol (10:2 FTOH)	865-86-1	
2H,2H,3H,3H-Perfluoroundecanoic acid (H4PFUnA)	34598-33-9	
Perfluorocyclohexanol 8:2 (8:2 FTOH)	678-39-7	
1H,1H,2H,2H-perfluorotetradecan-1-ol (12:2 FTOH)	39239-77-5	
1H,1H,2H,2H-Perfluorododecanesulphonic acid (10:2 FTS)	120226-60-0	
1H,1H,2H,2H-Perfluorododecyl iodide (10:2 FTI)	2043-54-1	
1H,1H,2H,2H-Perfluorotetradecyl iodide (12:2 FTI)	30046-31-2	
PFHxA and its salts	Various as below:	25 ppb total
Perfluorohexanoic Acid (PFHxA, C6-PFCA)	307-24-4	PFHxA and its salts Total 25 ppb (prohibited from use)
PFHxA-related Substances	Various as below:	1000 ppb total
1H,1H,2H,2H-Perfluorooctyl acrylate (6:2 FTA)	17527-29-6	PFHxA-related substances Total 1000 ppb (prohibited from use)
1H,1H,2H,2H-Perfluorooctyl methacrylate (6:2 FTMA)	2144-53-8	
1H,1H,2H,2H-Perfluorooctanesulfonic acid (6:2 FTS)	27619-97-2	
1H,1H,2H,2H-Perfluorooctanol (6:2 FTOH)	647-42-7	

24

Pesticides and Herbicides

2-(2,4,5-trichlorophenoxy) propionic acid, its salts and compounds; 2,4,5-TP	93-72-1	0.5 ppm each	All materials: EN ISO 15913:2003 or EPA 8081/EPA 8151A or BVL L 00.00-34:2010-09
2,4,5-Trichlorophenoxyacetic acid (2,4,5-T)	93-76-5	0.5 ppm each	
2,4-Dichlorophenoxyacetic acid (2,4-D)	94-75-7	0.5 ppm each	
Aldrine	309-00-2	0.5 ppm each	
Azinophosmethyl	86-50-0	0.5 ppm each	
Azinophosethyl	2642-71-9	0.5 ppm each	
Bromophos-ethyl	4824-78-6	0.5 ppm each	
Captafol	2425-06-1	0.5 ppm each	
Carbaryl	63-25-2	0.5 ppm each	
Chlorbenzilat	510-15-6	0.5 ppm each	
Chlordane	57-74-9	0.5 ppm each	
Chlordimeform	6164-98-3	0.5 ppm each	
Chlorfenvinphos	470-90-6	0.5 ppm each	
Chlorthalonil	1897-45-6	0.5 ppm each	
Coumaphos	56-72-4	0.5 ppm each	
Cyfluthrin	68359-37-5	0.5 ppm each	
Cyhalothrin	91465-08-6	0.5 ppm each	
Cypermethrin	52315-07-8	0.5 ppm each	
S,S,S-Tributyl phosphorothioate (Tribufos)	78-48-8	0.5 ppm each	
Deltamethrin	52918-63-5	0.5 ppm each	
p,p'-DDD	72-54-8	0.5 ppm each	
o,p'-DDD	53-19-0	0.5 ppm each	
p,p'-DDE	72-54-8	0.5 ppm each	
o,p'-DDE	3424-82-6	0.5 ppm each	
p,p'-DDT	50-29-3	0.5 ppm each	
o,p'-DDT	789-02-6	0.5 ppm each	
Diazinone	333-41-5	0.5 ppm each	
Dichlofluanide	1085-98-9	0.5 ppm each	
Dichloroprop	120-36-5	0.5 ppm each	
Dicofol	115-32-2	0.5 ppm each	
Dicrotophos	141-66-2	0.5 ppm each	
Dieldrine	60-57-1	0.5 ppm each	
Dimethoate	60-51-5	0.5 ppm each	
Dinoseb, its salts and acetate	88-85-7	0.5 ppm each	
DTTB (4, 6-Dichloro-7 (2,4,5-trichlorophenoxy)-2-Trifluoro methyl benzimidazole)	63405-99-2	0.5 ppm each	
Endosulfan	115-29-7	0.5 ppm each	
Endosulfan I (alpha)	959-98-8	0.5 ppm each	
Endosulfan II (beta)	33213-65-9	0.5 ppm each	
Endrine	72-20-8	0.5 ppm each	
Esfenvalerate	66230-04-4	0.5 ppm each	
Ethylendibromid	106-93-4	0.5 ppm each	
Ethylparathione; Parathion	56-38-2	0.5 ppm each	
Fenvalerate	51630-58-1	0.5 ppm each	
Halogenated naphthalenes, including polychlorinated naphthalenes (PCNs)	Various	0.5 ppm each	
Heptachlor	76-44-8	0.5 ppm each	
Heptachloroepoxide	1024-57-3	0.5 ppm each	
Hexabromobiphenyl	36355-01-8	0.5 ppm each	
α-Hexachlorocyclohexane (with & without Lindane)	319-84-6	0.5 ppm each	
β-Hexachlorocyclohexane (with & without Lindane)	319-85-7	0.5 ppm each	
γ-Hexachlorocyclohexane (with & without Lindane)	319-86-8	0.5 ppm each	
Hexachlorobenzene	118-74-1	0.5 ppm each	
Isodrine	465-73-6	0.5 ppm each	
Kelevane	4234-79-1	0.5 ppm each	

	Kepone	143-50-0	0.5 ppm each	
	Lindane	58-89-9	0.5 ppm each	
	Malathione	121-75-5	0.5 ppm each	
	MCPA	94-74-6	0.5 ppm each	
	MCPB	94-81-5	0.5 ppm each	
	Mecoprop	93-65-2	0.5 ppm each	
	Metamidophos	10265-92-6	0.5 ppm each	
	Methoxychlor	72-43-5	0.5 ppm each	
	Mirex	2385-85-5	0.5 ppm each	
	Monocrotophos	6923-22-4	0.5 ppm each	
	Parathion-methyl	298-00-0	0.5 ppm each	
	Pentachloroanisole	1825-21-4	0.5 ppm each	
	Phosdrin/Mevinphos	7786-34-7	0.5 ppm each	
	Perthane	72-56-0	0.5 ppm each	
	Propethamphos	31218-83-4	0.5 ppm each	
	Profenophos	41198-08-7	0.5 ppm each	
	Quinalphos	13593-03-8	0.5 ppm each	
	Quintozene	82-68-8	0.5 ppm each	
	Strobane	8001-50-1	0.5 ppm each	
	Telodrine	297-78-9	0.5 ppm each	
	Toxaphene	8001-35-2	0.5 ppm each	
	Tolyfluanide	731-27-1	0.5 ppm each	
	Trifluraline	1582-09-8	0.5 ppm each	
25	Phthalates			
	Di-Iso-nonylphthalate (DINP)	28553-12-0	500 ppm each, 250ppm for Children's PU and Leather	Sample preparation for all materials: CPSC-CH-C1001-09.4 Measurement: Textiles: GC/MS, EN ISO 14389:2022 (8.1 Calculation based on weight of print only; 8.2 Calculation based on weight of print and textile if print cannot be removed). All materials except textiles: GC/MS
	Di-n-octylphthalate (DNOP)	117-84-0	500 ppm each, 250ppm for Children's PU and Leather	
	Di(2-ethylhexyl)-phthalate (DEHP)	117-81-7	500 ppm each, 250ppm for Children's PU and Leather	
	Diisodecylphthalate (DIDP)	26761-40-0	500 ppm each, 250ppm for Children's PU and Leather	
	Butylbenzylphthalate (BBP)	85-68-7	500 ppm each, 250ppm for Children's PU and Leather	
	Dibutylphthalate (DBP)	84-74-2	500 ppm each, 250ppm for Children's PU and Leather	
	Diisobutylphthalate (DIBP)	84-69-5	500 ppm each, 250ppm for Children's PU and Leather	
	Di-n-hexylphthalate (DnHP)	84-75-3	500 ppm each, 250ppm for Children's PU and Leather	
	Diethylphthalate (DEP)	84-66-2	500 ppm each, 250ppm for Children's PU and Leather	
	Dimethylphthalate (DMP)	131-11-3	500 ppm each, 250ppm for Children's PU and Leather	
	Di-n-pentyl phthalate (DPENP)	131-18-0	500 ppm each, 250ppm for Children's PU and Leather	
	Dicyclohexyl phthalate (DCHP)	84-61-7	500 ppm each, 250ppm for Children's PU and Leather	
	1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich	71888-89-6	500 ppm each, 250ppm for Children's PU and Leather	
	Bis(2-methoxyethyl) phthalate	117-82-8	500 ppm each, 250ppm for Children's PU and Leather	
	Diisopentyl phthalate (DIPP)	605-50-5	500 ppm each, 250ppm for Children's PU and Leather	
	Dipropyl phthalate (DPRP)	131-16-8	500 ppm each, 250ppm for Children's PU and Leather	
	Diisooctyl phthalate (DIOP)	27554-26-3	500 ppm each, 250ppm for Children's PU and Leather	
	1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear	68515-50-4	500 ppm each, 250ppm for Children's PU and Leather	
	Diisohexyl phthalate (DIHxP)	71850-09-4	500 ppm each, 250ppm for Children's PU and Leather	
	1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters (DHNUP)	68515-42-4	500 ppm each, 250ppm for Children's PU and Leather	
	1,2-Benzenedicarboxylic acid, dipentyl ester, branched and linear	84777-06-0	500 ppm each, 250ppm for Children's PU and Leather	
	1,2-Benzenedicarboxylic acid, di-C6-10-alkyl esters or mixed decyl and hexyl and octyl diesters with ≥ 0.3% of dihexyl phthalate; 1,2-Benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters; 1,2-Benzenedicarboxylic acid, di-C6-10-alkyl esters	68648-93-1	500 ppm each, 250ppm for Children's PU and Leather	
		68515-51-5		
	n-Pentyl-isopentylphthalate (nPIPP)	776297-69-9	500 ppm each, 250ppm for Children's PU and Leather	
	Bis(2-ethylhexyl) tetrabromophthalate	26040-51-7	500 ppm each, 250ppm for Children's PU and Leather	
	Bis(2-propylheptyl) phthalate (DPHP)	53306-54-0	Reporting only	
			Total: 1000 ppm, 250ppm for Children's PU and Leather	
26	Polycyclic Aromatic Hydrocarbons (PAHs)			
	Acenaphptene	83-32-9	No individual restriction	All materials: AFPS GS 2019 or EN 17132:2019 or ISO 16190:2021
	Acenaphthylene	208-96-8	No individual restriction	
	Anthracene	120-12-7	No individual restriction	
	Benzo(g,h,i)perylene	191-24-2	No individual restriction	
	Fluorene	86-73-7	No individual restriction	
	Fluoranthene	206-44-0	No individual restriction	
	Indeno(1,2,3-cd)pyrene	193-39-5	No individual restriction	
	Naphthalene	91-20-3	No individual restriction	
	Phenanthrene	85-01-8	No individual restriction	
	Pyrene	129-00-0	No individual restriction	
	Benzo(a)anthracene	56-55-3	1 ppm each	
	Benzo(a)pyrene	50-32-8	1 ppm each	
	Benzo(b)fluoranthene	205-99-2	1 ppm each	
	Benzo[e]pyrene	192-97-2	1 ppm each	
	Benzo[j]fluoranthene	205-82-3	1 ppm each	
	Benzo(k)fluoranthene	207-08-9	1 ppm each	
	Chrysene	218-01-9	1 ppm each	
	Dibenzo(a,h)anthracene	53-70-3	1 ppm each	
			1 ppm each	
27	Quinoline			
	Quinoline	91-22-5	50 ppm	All materials: DIN 54231:2022 with methanol extraction at 70° C
28	Solvents and Residuals			
	Dimethylformamide (DMFa)	68-12-2	500 ppm	Textiles: EN 17131-1:2025 All other materials: ISO 16189:2021
	Formamide	75-12-7	1000 ppm Clothing and Footwear 200 ppm All Other Items including play mats, baby mats and yoga mats	
	Dimethylacetamide (DMAC)	127-19-5	1000 ppm	
	N-Methyl-2-pyrrolidone (NMP)	872-50-4	1000 ppm	

29	UV Absorbers / Stabilizers			
	UV 320	3846-71-7	1000 ppm	ISO 24040:2022 with extraction in THF, analysis by GC/MS Note: Stabilized THF should be used for extraction
	UV 326	3896-11-5	1000 ppm	
	UV 327	3864-99-1	1000ppm	
	UV 328	25973-55-1	100 ppm	
	UV 329	3147-75-9	1000 ppm	
	UV 350	36437-37-3	1000 ppm	
	Drometrizole	2440-22-4	Reporting only	
30	Volatile Organic Compounds (VOCs)			
	Benzene	71-43-2	5 ppm	For general VOC screening: GC/MS headspace 45 minutes at 120° C
	Carbon Disulfide	75-15-0	Total: 500 ppm (Excluding Benzene)	
	Carbon Tetrachloride	56-23-5		
	Chloroform	67-66-3		
	Cyclohexanone	108-94-1		
	1,2-Dichloroethane	107-06-2		
	1,1-Dichloroethylene	75-35-4		
	Ethylbenzene	100-41-4		
	Pentachloroethane	76-01-7		
	1,1,1,2- Tetrachloroethane	630-20-6		
	1,1,2,2- Tetrachloroethane	79-34-5		
	Tetrachloroethylene (PERC)	127-18-4		
	Toluene	108-88-3		
	1,1,1- Trichloroethane	71-55-6		
	1,1,2- Trichloroethane	79-00-5		
	Trichloroethylene	79-01-6		
	Xylenes (meta-, ortho-, para-)	1330-20-7		
	Xylenes (meta-, ortho-, para-)	108-38-3		
	Xylenes (meta-, ortho-, para-)	95-47-6		
	Xylenes (meta-, ortho-, para-)	106-42-3		
	1,2-Dichlorobenzene	95-50-1		
	1,4-Dichlorobenzene	106-46-7		
	1-Methyl-2-pyrrolidione	872-50-4		
	2-phenyl-2-propanol	617-94-7		
	Acetophenone	98-86-2		
	Formamide	75-12-7		
	N,N-Dimethylacetamide (DMAC)	127-19-5		
	Naphthalene	91-20-3		
	N-N-Dimethylformamide (DMFa)	68-12-2		
	Styrene	100-42-5		
	1,2,3-trichloropropane	96-18-4		
	1,2,Dichloropropane	78-87-5		
	2-Ethoxyethyl acetate	111-15-9		
	2-Ethylhexane acid	149-57-5		
	Aniline	62-53-3		
	Bis(2-methoxyethyl)ether	111-96-6		
	Isophorone	78-59-1		
	Phenol	108-95-2		
	THF	109-99-9		
	1-bromopropane	106-94-5		
	1-PG2MEA 1-Propanol,2-methoxy-, acetate	70657-70-4		
	2-(2-Methoxyethoxy)ethanol	111-77-3		
	2-ethoxyethanol	110-80-5		
2-Methoxyethanol EGME (ethylene glycol monomethyl ether)	109-86-4			
2-Methoxypropan-1-ol	1589-47-5			
EGDME (Ethylene glycol dimethyl ether)	110-71-4			
EGMEA (Ethylene glycol monomethyl ether acetate)	110-49-6			
Hexachloroethane	67-72-1			
Merhylene chloride (dichloromethane)	75-09-2			
n-hexane	110-54-3			
TEGDME (Triethylene glycol dimethyl ether)	112-49-2			
31	Polyvinyl Chloride (PVC)			
	Polyvinyl Chloride (PVC)	9002-86-2	Prohibited from use	FTIR analysis
32	Cyclosiloxanes			
	Octamethylcyclotetrasiloxane (D4)	556-67-2	1000 ppm each	All materials: Ultrasonic extraction with tert-Butyl methyl ether (TBME) or acetone for 30 min at 40° C then GC/MS
	Decamethylcyclopentasiloxane (D5)	541-02-6		
	Dodecamethylcyclohexasiloxane (D6)	540-97-6		